

Product data sheet



Product: 6000GP
MIRO® 6 - Semi-Specular

4700/0415/003/11.15

Alloy	¹	Al 99,7 Mg 0,50 Cu
Hardness	²	3/4 hard
Treatment front side	(S1)	brightened, anodised and PVD-coated
Treatment reverse side	(S2)	anodised
Coating system	(S1)	PVD - based on Al 99,99
Iridescence assessment	(S1)	absolutely free of interference colours

Delivery options

in form of		Coil, strip, sheet, blanks
Thickness from/to	[inch]	0.0118 - 0.0315
Width up to	[inch]	49.2126

Optical Values

Total light reflection	[%]	≥ 94	DIN 5036-3 (U-Globe) (8°)
Diffuse light reflection	[%]	40 - 58	DIN 5036-3 (U-Globe) (8°)
Brightness 60° along	[-]	68 - 82	ISO 7668 (60°)
Brightness 60° across	[-]	66 - 80	ISO 7668 (60°)
Reflectance class		A	DIN EN 16268

Mechanical Properties

Yield strength Rp 0,2	[ksi]	≥ 17.4
Tensile strength Rm	[ksi]	21.8 - 27.6
Elongation A50	[%]	≥ 1
Deformation/Bending/Bending radius		≥ 1.5 x gauge of material

Tolerances

Thickness from/to	[inch]	0.0118 - 0.0197 ± 0.0016
	[inch]	0.0201 - 0.0236 ± 0.0020
	[inch]	0.0240 - 0.0315 ± 0.0024
Width/Coil up to	[inch]	+ 0.1181 / - 0.0000
Width Slit Coil	[inch]	± 0.0079 standard
Longitudinal Curvature Length	[inch]	≤ 0.0394 on a measuring length of 39.3700
	[inch]	0.0000 - 23.6220 + 0.0394 / - 0.0000
	[inch]	23.6221 - 59.0551 + 0.0591 / - 0.0000
	[inch]	59.0552 - 98.4252 + 0.0984 / - 0.0000
Flatness	[inch]	98.4253 - 137.7953 + 0.1378 / - 0.0000
	[%]	1 % of wavelength, max. 0.3150 [inch]
Transversal Divergency	[inch]	≤ 0.0591 (D1-D2) other tolerances on request

Protective Film

Protective Film Type	[-]	PE - Film
Protective Film Thickness	[µm]	50 - 60

¹ based on DIN EN 573-3 (Aluminium), DIN EN 13599 (Copper) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium), DIN EN 1652 (Copper) resp. Rolling mill standard



Product data sheet



4700/0415/003/11.15

The optical properties advised above are based on material thicknesses from 0.0157 to 0,0197 inch

¹ based on DIN EN 573-3 (Aluminium), DIN EN 13599 (Copper) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium), DIN EN 1652 (Copper) resp. Rolling mill standard

17.02.2021 09:01:08 Valid only on print date

